

Annex n.1F to test report n. 1803032-003

DETAILS OF TEST RESULTS

Test carried out according to UNI 9175: 1987 + UNI 9175 FA-1:1994
Reaction to fire of upholstered furnitures by applying a small flame

Article description: **CARABU CRIB 5**

Declared composition: 36% POLYESTER □ 26% ACRYLIC □ 18% POLYESTER FR □ 11% POLYAMIDE □ 9% VISCOSE

Sample pretreatment: sample wasn't subjected to any pretreatment, as required by the customer

Conditioning of test specimen: 20 ± 2 °C, 65 ± 5 % r.h.

Date of test: 04/06/2018

	flame application time 20 s	flame application time 80 s	flame application time 140 s
sample series	Post-combustion time (s)	Post-combustion time (s)	Post-combustion time (s)
FIRST SERIES	17	20	20
SECOND SERIES	15	21	19
THIRD SERIES	-	-	-
RESULT	POSITIVE	POSITIVE	POSITIVE

SAMPLE MEETS THE CLASS 1.IM REQUIREMENTS

Notes:

The result of the test is ☐ POSITIVE ☐ if the afterflame time is less than 120 s and the specimen is not completely burnt.

The test of third series is necessary if the results between the first and the second series are different.

Classification criteria:

3.IM class:

is attributed to the sample if the test is successful only with the flame application time of 20 s

2.IM class:

is attributed to the sample if the test is successful with the flame application time of 20 s and 80 s

1.IM class:

is attributed to the sample if the test is successful with the flame application time of 20 □ 80 and 140 s

NOT classifiable: is attributed to the sample if the test fails the flame application time of 20 s

Technical Head

Enrica Baldini



TEST REPORT

Report nr.: **1803032-003**
Report date: **05-giu-18**
Acceptance code: **1803032**
Acceptance date: **04-giu-18**
Start test date: **04-giu-18**
End test date: **05-giu-18**
References: **---**

Customer code: 07537

To:
ANTECUIR SL
A.vda del Ferrocarril, s/n
03830 MURO DE ALCOY - ALICANTE
ESPANA

To the attention of:
sig. Antonio Aguilar

Tel.nr: +34 610 435792

Fax.nr.: .

Article description: **CARABU CRIB 5**
Declared composition: **36% Polyester - 26% Acrylic - 18% Polyester FR - 11% Polyamide - 9% Viscose**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
15036 REACTION TO FIRE OF UPHOLSTERED FURNITURES BY APPLYING A SMALL FLAME		
Method: UNI 9175 (1987) + A1 (1994)		
Instrument: Small Test Rig and burner for Flammability test		
Sample pretreatment:		
sample wasn't subjected to any pretreatment		
Upholstery filling test result (flame time application: 20 s)		Not done
NOTE: In absence of effective upholstery filling, the test has been carried out using a FLAME RETARDANT POLYURETHANE FOAM with a density of 30 kg/m ³ (HR35D) as filling of the upholstered seating. This foam meets the test requirements for the upholstery filling (test on upholstery filling - without outer cover material - 20 s of flame time application). The test result could be different using another type of filling material.		
Upholstery composite test result (flame time application: 20 s)		POSITIVE
Upholstery composite test result (flame time application: 80 s)		POSITIVE
Upholstery composite test result (flame time application: 140 s)		POSITIVE
TEST RESULT:		SAMPLE MEETS THE CLASS 1.IM REQUIREMENT
Annex n.:		1F

Other references:
D.M. 26 June 1984 - D.M. 3 September 2001.

This test is not valid for Italian Ministerial approval.

Report nr.

1803032-003

TEST

M.U.

RESULTS

----- END OF TEST REPORT -----

Technical Head

Enrica Baldini

