

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 13, 2024

Mr. Rafael Pascual
AQUACLEAN USA INC.
834 Huffman Street
Greensboro, NC 27405

Reference: Laboratory Test Report
Lab Identification No. 58525
Invoice No. 89815

Dear Mr. Pascual:

One (1) fabric sample, identified as **MYSTIC-AC-SF 324**, was received and tested in accordance with the California Technical Bulletin 117-2013, Section 1, Cover Fabric Test. The results are as follows:

Test Results

<u>Vertical Char Lengths</u>		
15mm	15mm	16mm


The sample submitted **meets** the requirements of the above standard. There were no ignitions or smoldering after 45 minutes on any of the three specimens tested. In addition, none of the three test specimens displayed a char which was greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

“We Test Per Your Request”

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

February 13, 2024

Mr. Rafael Pascual
AQUACLEAN USA INC.
834 Huffman Street
Greensboro, NC 27405

Reference: Laboratory Test Report
Lab Identification No. 58525
Invoice No. 89815

Dear Mr. Pascual:

One (1) fabric sample, identified as **MYSTIC-AC-SF 324**, was received and tested in accordance with the NFPA 260, "Cigarette Ignition Resistance of Components of Upholstered Furniture, 2024 Edition", (Cover Fabric Test). The results are as follows:

Test Results

Vertical Char Lengths

17mm

15mm

16mm

*Date Tested: February 13, 2024

*Conditioned minimum of 4 hours @ 70±5°F and >65% RH

The sample submitted **meets** the requirements of the above standard and may be considered a **Class I Cover Fabric**. There were no ignitions on any of the three specimens tested. In addition, none of the three test specimens displayed a vertical char which was equal to or greater than 45 mm.

Sincerely,

Brian S. Dement

BSD/mr

