



Centro Tessile Serico Sostenibile Srl
 via Castelnuovo, 3 - 22100 Como Italia
 Pho +39 031 3312111/120 Fax: +39 0313312149
 Amministrazione/Contabilità +39 031 3312102-154
 P. IVA - C.F. 03900470133
 Capitale sociale euro 600000,00 iv
 mailbox@textilecomo.com
 www.textilecomo.com

Test Report No.: **2501030-001**

Date Test Report **05-mar-25**
 Acceptance: **2501030**
 Arrival date sample **21-feb-25**
 Start date test **21-feb-25**
 End date test **05-mar-25**
 References:

Customer Code 08480

Dear:
INTERFABRICS S.L.
 CTRA. ALICANTE, 76
 03801 ALCOY - ALICANTE SPAIN

C.a. Mr. Antonio Jesús Fernández

Phone: 678601907

Sampling Mode: Sampling by Customer

[C] Item: **COLECCION RUSTIKA**
 (ALPINE, ANGORA, ARENDAL, BALTIC, BELAIR, CAROUSEL, FABIA, NORWAY, OSLO, REBANO, SIMBEL)
 [C] Declared Composition: **35% CO - 27% PL - 18% PAC - 15% PA - 5% Other Fibers**
 [C] End use: **upholstery**
 [C] Typology: **fabric - flock**
 [C] Note: **E18857**
 Return: **no requested**

Test Results

Test	Method	U.M.	Result
15036 REACTION TO FIRE OF FURNITURE BY APPLYING A SMALL FLAME	UNI 9175:1987 + A1:1994		.
Start date test	04/03/2025		
End date test	05/03/2025		
Instrument: Small Test Rig and burner			
Pretreatment carried out			None
Upholstery filling test result (flame 20 s)			.
NOTE: In absence of effective upholstery filling, the test has been carried out using a FLAME RETARDANT POLYURETHANE FOAM with a density of 35 kg/m³ (HR35D) as filling of the upholstered seating. This foam meets the test requirements for the upholstery filling (test on upholstery filling - without outer cover material - 20 s of flame time application). The test result could be different using another type of filling material.			
Upholstery filling test result (flame 20 s)		-	POSITIVE
Upholstery test result (flame 80 s)		-	POSITIVE
Upholstery test result (flame 140 s)		-	POSITIVE
TEST RESULT			SAMPLE MEET THE CLASS 1.IM
Deviations from the method			None
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
 This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
 [C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 03900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com

Test Report No.: **2501030-001**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager
Fausto Albonico

END OF REPORT

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.