



**Centro Tessile Serico Sostenibile Srl**  
 via Castelnuovo, 3 - 22100 Como Italia  
 Pho +39 031 3312111/120 Fax: +39 0313312149  
 Amministrazione/Contabilità +39 031 3312102-154  
 P. IVA - C.F. 003900470133  
 Capitale sociale euro 600000,00 iv  
 mailbox@textilecomo.com  
 www.textilecomo.com

Test Report No.:	<b>2207507-001</b>	
Date Test Report	<b>02-nov-22</b>	Customer Code 08480
Acceptance:	<b>2207507</b>	Dear:
Arrival date sample	<b>27-ott-22</b>	<b>INTERFABRICS S.L.</b>
Start date test	<b>27-ott-22</b>	CTRA. ALICANTE, 76
End date test	<b>02-nov-22</b>	03801 ALCOY - ALICANTE SPAIN
References:		C.a. Mr. Antonio Jesús Fernández
		Phone: 678601907
Sampling Mode:	Sampling by Customer	
[C] Item:	VENICE-AC-INFR-CRIB5	
[C] Declared Composition:	71% Polyester - 18% MAC - 8% recycled cotton - 3% Polyamide	
[C] End use:	Upholstery	
[C] Typology:	dyeing article	
Note:	red phosphorus: B70720	
Return:	No requested	

## Test Results

Test	Method	U.M.	Result
<b>15036 REACTION TO FIRE OF FURNITURE BY APPLYING A SMALL FLAME</b>	<b>UNI 9175:1987 + A1:1994</b>		.
<b>Start date test</b>	28/10/2022		
<b>End date test</b>	02/11/2022		
<b>Instrument:</b> Small Test Rig and burner			
Pretreatment carried out			none, as required
Upholstery filling test result (flame 20 s)			not done
NOTE: In absence of effective upholstery filling, the test has been carried out using a FLAME RETARDANT POLYURETHANE FOAM with a density of 35 kg/m <sup>3</sup> (HR35D) as filling of the upholstered seating. This foam meets the test requirements for the upholstery filling (test on upholstery filling - without outer cover material - 20 s of flame time application). The test result could be different using another type of filling material.			
Upholstery filling test result (flame 20 s)		-	POSITIVE RESULT
Upholstery filling test result (flame 80 s)		-	POSITIVE RESULT
Upholstery filling test result (flame 140 s)		-	POSITIVE RESULT
TEST RESULT			sample
Deviations from the method			SAMPLE MEET THE CLASS 1.IM REQUIREMENTS OF UNI 9175
Note: to assess the ignitability of this sample, the test has been carried out using a fire-retardant polyurethane foam with a density of 35 kg/m <sup>3</sup> as filling of the upholstered seating. The test result could be different using another type of filling material.			
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.  
 This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.  
 [C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com

Test Report No.: **2207507-001**

Test	Method	U.M.	Result
------	--------	------	--------

**The Laboratory Manager**  
Fausto Albonico

-----  
**END OF REPORT**  
-----

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.  
This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.  
[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.